

DuroStrut™

Fiberglass/Composite Strut & Support Systems

Create new support systems
or add to existing cable tray.
Works with Enduro cable trays
as well as other systems.
Includes all the items necessary
to fabricate an unlimited
number of configurations...
wall mounted, floor mounted,
or hanging!

BENEFITS & QUALITIES

Corrosion Resistance –
No rusting, peeling, or flaking.

High Strength –
Strength to weight ratios that surpass
equivalent steel products.

Lightweight –
Low specific gravity...easy to handle.

Fire Retardant –
In accordance with ASTM E-84 Class I.

UV Resistant –
Contains an ultraviolet inhibiting additive
in resin and a protective veil.

Low Thermal Conductivity –
Will not transfer heat or cold
like metal products.

Cost Effective –
Extremely long life...low life cycle costs.


Easy to Install and Access –
Easy to cut and custom fabricate.

Non-interfering/Non-magnetic –
Transparent to radio waves.


These products are available from




CHANNEL FRAMING




EC-158D



- For use in tray support systems, electrical conduit and tray rungs for tying down cable.
- Available in 10 Ft. and 20 Ft. lengths.
- Refer to Table 1 on Page 6 for Loading Information.



EC-158




EC-10

Catalog No. Lbs./Ft.	Polyester Resin		
	EC-10	EC-158	EC-158D
0.47	0.68	1.36	
Catalog No. Lbs./Ft.	Vinyl Ester Resin		
	EC-VE-10	EC-VE-158	EC-VE-158D
0.47	0.68	1.36	

STRUT POST BASE

- Available for both single and double strut.


PB-1V




- Single - Available in Vinyl Ester
Catalog No. PB-1V

- Single - Available in Polyester or Polyurethane
Catalog No. PBS-PE (Polyester) / PBS-PU (Polyurethane)

- Double - Available in Polyester or Polyurethane
Catalog No. PBD-PE (Polyester) / PBD-PU (Polyurethane)




PBD



PBS

PUNCHED CHANNEL FRAMING

- Available in Polyester and Vinyl Ester resin types.
- Standard Lengths: 10 Ft. and 20 Ft.
- 9/16" holes on 2" centers.
- Replaces drilled strut.



Catalog No. Resin	EC-10H Polyester	EC-158H Polyester	EC-VE-10H Vinyl Ester	EC-VE-158H Vinyl Ester
----------------------	---------------------	----------------------	--------------------------	---------------------------


DuroStrut CONNECTOR PLATES

- Based on individual applications, changes may be required on dimension and thickness of material. Please consult factory.
- Holes are drilled to accept $\frac{3}{8}$ " and $\frac{1}{2}$ " bolts.


For Vinyl Ester Connector Plates, insert the letters "VE" as indicated in this example:

CP-100 (Polyester)


CP-VE-100 (Vinyl Ester)




CP-100




CP-101




CP-102




CP-103




CP-104




CP-105




CP-109




CP-110




CP-111




CP-112




CP-113




CP-114




CP-115




CP-116




CP-117




CP-118



CP-119




CP-120




CP-205


Note: Flat washer not required for CP-205.




CP-209




CP-210




CP-211



CP-226



CP-405



Universal Angle CP-501

CP-501 (Polyester)

CP-PU-501 (Polyurethane)

CP-NY-501 (Nylon)

- Available in Polyester, Polyurethane (alternate to Vinyl Ester), and Nylon.

EnduroSeal FIELD CUTTING SEALANT


- Seals exposed fibers after any field cuts.
- Restores gloss and luster to weathered fiberglass.
- Seals exposed FRP threads after installation of DuroThread threaded rod and hex nuts.
- For Polyester and Vinyl Ester resin products.
- Clear color.



Meets **NSTA and UPS** requirements for sea and ground transportation.


Catalog No. Container | ES-Q Quart Can | ES-G Gallon Can

WINDOW CLAMP



- Stainless Steel set screw included.

Part No: WC-158



enduro

DuroThread™ Fastener & Hanging Systems


DuroThread™ is an exceptionally strong non-metallic mechanical fastener system with outstanding shear and tensile strengths. This makes the DuroThread™ fastener system an excellent choice for all structural, mechanical and electrical applications where fasteners must be corrosion resistant and/or non-conductive.

It is NOT recommended that FRP threaded rod be used in conjunction with steel or PVC coated steel beam clamps or nuts. Thread shear could occur due to insufficient thread engagement.

Refer to DuroThread™ Installation Guide on page 6, and Typical Properties for Threaded Rod on page 8.


FRP THREADED RODS

- Vinyl Ester resin.
- Available in 8 Ft. lengths.



Catalog No.	Size	Weight Lbs./Ft.
TR-FRP-038	3/8"-16 UNC	0.07
TR-FRP-050	1/2"-13 UNC	0.12
TR-FRP-0625	5/8"-11 UNC	0.18
TR-FRP-075	3/4"-10 UNC	0.28
TR-FRP-100	1"-8 UNC	0.50


FRP FLAT WASHERS



Catalog No.	Size	Weight Lbs./Ft.
FW-FRP-038	3/8"-16 UNC	1.3
FW-FRP-050	1/2"-13 UNC	1.3
FW-FRP-0625	5/8"-11 UNC	1.3
FW-FRP-075	3/4"-10 UNC	1.3
FW-FRP-1000	1"-8 UNC	1.3


BEAM CLAMPS

- Ultimate Load = 300 Lbs.
- Recommended safety factor = 3.
- SS set screws included with clamps.



Description	Catalog No.
Single for 3/8" FRP Threaded Rod	BCS-3/8
Single for 1/2" FRP Threaded Rod	BCS-1/2
Double for 3/8" FRP Threaded Rod	BCD-3/8
Double for 1/2" FRP Threaded Rod	BCD-1/2


FRP HEX NUTS



- Vinyl Ester resin.

Catalog No.	Size	Weight Lbs./Ft.	τ = In. (mm)	A = In. (mm)
FN-FRP-038	3/8"-16 UNC	2.43	5/8 (16)	7/8 (22)
FN-FRP-050	1/2"-13 UNC	2.17	5/8 (16)	7/8 (22)
FN-FRP-0625	5/8"-11 UNC	6.05	7/8 (22)	1 1/4 (32)
FN-FRP-075	3/4"-10 UNC	5.42	7/8 (22)	1 1/4 (32)
FN-FRP-1000	1"-8 UNC	20.49	1 1/4 (32)	2 (51)

FRP ROD COUPLERS




- Vinyl Ester resin.

IMPORTANT:

Minimum thread engagement must be 3/4" per side.

Catalog No.	Size	Weight Lbs./Ft.	τ = In. (mm)
RC-FRP-038	3/8"-16 UNC	7.80	2 (51)
RC-FRP-050	1/2"-13 UNC	7.00	2 (51)
RC-FRP-0625	5/8"-11 UNC	13.73	2 (51)
RC-FRP-075	3/4"-10 UNC	12.66	2 (51)
RC-FRP-1000	1"-8 UNC	44.03	2 3/4 (70)


FRP CHANNEL NUTS



- Vinyl Ester resin.
- Channel Nuts are self locking and designed for use with EC-158 and EC-158D DuroStrut™ only (see page 1).
- Resistance to slip = 450 Lbs. per bolt.
- Pull out strength = 700 Lbs. per bolt.
- Recommended safety factor = 3.

Catalog No.	Size	Weight Lbs./Ft.	τ = In. (mm)
CN-038	3/8"-16 UNC	5.46	1 1/16 (27)
CN-050	1/2"-13 UNC	5.00	1 1/16 (27)

"NON-METALLIC" UNIVERSAL PIPE CLAMPS



- For rigid, PVC coated steel, PVC Schedule 40 & 80 and fiberglass conduit.
- Made from a toughened grade of glass reinforced thermoplastic polyester resin.
- Standard fasteners are nylon slotted hex bolt and nut. Recommended for horizontal use as shown. For vertical placement please contact factory.

- Packaged twenty sets per bag.
- If stainless steel fasteners are preferred, indicate by adding the letter "S" after the catalog number (Example: PC-1609S).


* Includes nylon bolt.



CONDUIT SWIVEL CLAMP

- This allows an easy transition to/from conduit and FRP cable tray.

- Please substitute Enduro cable tray type when ordering (Example: TD=EHL6).
- Pipe clamps are a separate order item. See above.



Catalog No. ECTC-(TD)-VE = Vinyl Ester


Catalog No. ECTC-(TD) = Polyester

VERTICAL TRAY HANGER SUPPORT

Tray Depth
Inches (mm) Catalog No.

Polyester Resin	
3 (76)	VH-3P
4 (102)	VH-4P
6 (152)	VH-6P
8 (203)	VH-8P
Vinyl Ester Resin	
6 (152)	VH-6V


Note: Not available for EMZ6 tray.



FIBERGLASS CLEVIS HANGERS



- Vinyl Ester resin.
- Allowable loads have a 3:1 safety factor at 120°F.
- Insulation may be required at higher temperatures.
- Tolerance is 3/4" maximum.

Catalog No.	Nominal Dia. In.	Dimension Inches			Hanger Rod In.	Allowable Load Lbs.
		A	B	C		
CH-010	1	1 ⁵ / ₈	4 ³ / ₄	3	1/2	200
CH-015	1 1/2	2 ¹ / ₈	5 ⁵ / ₈	3 ³ / ₈	1/2	200
CH-020	2	2 ¹ / ₂	7	4 ³ / ₈	1/2	200
CH-025	2 1/2	3 ⁵ / ₁₆	6 ⁹ / ₁₆	4 ¹ / ₄	1/2	200
CH-030	3	3 ³ / ₄	7 ¹ / ₂	4 ¹ / ₄	1/2	300
CH-040	4	5 ¹ / ₈	9 ³ / ₄	5 ⁷ / ₈	1/2	400
CH-060	6	7 ³ / ₁₆	12 ³ / ₈	8	1/2	600
CH-080	8	9 ³ / ₈	15 ⁹ / ₁₆	10 ¹ / ₄	1/2	600
CH-100	10	11 ¹⁹ / ₃₂	19 ⁷ / ₈	12 ¹¹ / ₁₆	5/8	600
CH-120	12	13 ⁵ / ₈	22 ¹ / ₄	14	5/8	600
CH-140	14	15 ¹ / ₄	26 ³ / ₁₆	16 ³ / ₄	5/8	600



CABLE TRAY SUPPORT RACKS

Allowable load is based on a total load, uniformly distributed over the length of the rack. Safety factor = 2.0



Catalog No. Polyester Resin	Catalog No. Vinyl Ester Resin	Dimensions In.			Allowable Load Lbs.
		A	B	C	
SR1-6P	SR1-6V	10	12	10	1,600
SR1-9P	SR1-9V	13	12	10	1,100
SR1-12P	SR1-12V	16	12	10	850
SR1-18P	SR1-18V	22	12	10	725
SR1-24P	SR1-24V	28	12	10	480
SR2-24P	SR2-24V	28	23	21	750
SR2-30P	SR2-30V	34	26	24	750
SR2-36P	SR2-36V	40	29	27	750

Table 1 Beam and Column Data: Polyester and Vinyl Ester Resin Base

Beam Span or Column Height In. (mm)	Catalog No.	Maximum Allowable Uniform Beam Load		Deflection @ Maximum Allowable Uniform Beam Load		Uniform Load @ Maximum Deflection = 0.25 In. (6mm)		Uniform Load @ Maximum Deflection = 0.50 In. (13mm)		Maximum Allowable Column Load Lbs. (kg)
		Poly Lbs. (kg)	Vinyl Lbs. (kg)	Poly In. (mm)	Vinyl In. (mm)	Poly Lbs. (kg)	Vinyl Lbs. (kg)	Poly Lbs. (kg)	Vinyl Lbs. (kg)	
12 (305)	EC-10	790 (358)	990 (449)	0.11 (3)	0.12 (3)	• •	• •	• •	• •	2550 (1156)
	EC-158	1720 (780)	2150 (975)	0.07 (2)	0.07 (2)	• •	• •	• •	• •	3650 (1655)
	EC-158D	5080 (2301)	6350 (2880)	0.04 (1)	0.04 (1)	• •	• •	• •	• •	7300 (3111)
18 (457)	EC-10	530 (240)	670 (304)	0.24 (6)	0.27 (7)	• •	620 (281)	• •	• •	2350 (1066)
	EC-158	1150 (521)	1440 (653)	0.15 (4)	0.17 (4)	• •	• •	• •	• •	3370 (1528)
	EC-158D	5080 (2301)	4240 (1923)	0.09 (2)	0.10 (2)	• •	• •	• •	• •	6740 (3058)
24 (610)	EC-10	400 (181)	500 (227)	0.43 (11)	0.48 (12)	240 (109)	270 (122)	• •	• •	2070 (939)
	EC-158	860 (390)	1080 (490)	0.27 (7)	0.30 (8)	810 (367)	910 (412)	• •	• •	2960 (1342)
	EC-158D	2540 (1152)	3180 (1442)	0.16 (4)	0.17 (4)	• •	• •	• •	• •	5920 (2685)
30 (762)	EC-10	320 (145)	400 (181)	0.67 (17)	0.75 (19)	120 (54)	140 (63)	240 (109)	270 (122)	1710 (775)
	EC-158	690 (313)	870 (394)	0.42 (11)	0.48 (12)	410 (186)	460 (209)	• •	• •	2450 (1111)
	EC-158D	2040 (925)	2550 (1156)	0.24 (6)	0.27 (7)	2000 (907)	2350 (1066)	• •	• •	4900 (2222)
36 (914)	EC-10	270 (122)	340 (154)	0.98 (25)	1.10 (28)	70 (31)	80 (36)	140 (63)	160 (72)	1260 (571)
	EC-158	580 (263)	730 (331)	0.61 (15)	0.69 (19)	240 (109)	270 (122)	480 (217)	540 (245)	1800 (816)
	EC-158D	1700 (771)	2130 (966)	0.35 (9)	0.39 (10)	1220 (553)	1370 (621)	• •	• •	3600 (1633)
42 (1067)	EC-10	230 (104)	290 (131)	1.32 (34)	1.49 (38)	50 (22)	55 (25)	100 (45)	115 (52)	920 (417)
	EC-158	490 (222)	620 (281)	0.82 (21)	0.92 (23)	150 (68)	170 (77)	300 (136)	340 (154)	1320 (598)
	EC-158D	1460 (662)	1830 (830)	0.48 (12)	0.62 (16)	770 (349)	870 (394)	1510 (650)	1720 (780)	2640 (1197)
48 (1219)	EC-10	200 (91)	250 (113)	1.72 (44)	1.92 (49)	30 (13)	35 (16)	60 (27)	70 (31)	700 (317)
	EC-158	430 (195)	540 (245)	1.07 (27)	1.20 (30)	100 (45)	115 (52)	200 (90)	230 (104)	1010 (458)
	EC-158D	1270 (576)	1590 (721)	0.62 (16)	0.69 (17)	520 (236)	590 (267)	1040 (471)	1170 (530)	2020 (916)
60 (1524)	EC-10	160 (72)	200 (91)	2.68 (68)	2.99 (76)	20 (9)	23 (10)	40 (18)	45 (20)	180 (81)
	EC-158	350 (158)	400 (200)	1.70 (43)	1.91 (48)	60 (27)	70 (32)	120 (54)	135 (61)	260 (118)
	EC-158D	1020 (462)	1280 (580)	0.97 (25)	1.09 (28)	270 (122)	310 (140)	540 (245)	610 (276)	520 (235)
72 (1829)	EC-10	140 (63)	180 (81)	* *	* *	10 (4)	12 (5)	20 (9)	23 (10)	• •
	EC-158	290 (131)	370 (168)	2.44 (62)	2.78 (71)	30 (13)	34 (15)	60 (27)	70 (32)	• •
	EC-158D	850 (385)	1070 (485)	1.40 (35)	1.57 (40)	160 (72)	180 (81)	320 (145)	360 (163)	• •
84 (2134)	EC-10	120 (54)	150 (68)	* *	* *	NR	• •	12 (5)	15 (7)	• •
	EC-158	250 (113)	320 (145)	* *	* *	20 (9)	23 (10)	40 (18)	45 (20)	• •
	EC-158D	730 (331)	920 (417)	1.91 (48)	2.15 (55)	100 (45)	115 (52)	200 (90)	230 (104)	• •
96 (2438)	EC-10	100 (45)	130 (59)	* *	* *	NR	• •	• •	• •	• •
	EC-158	220 (100)	250 (113)	* *	* *	13 (6)	15 (7)	26 (12)	30 (13)	• •
	EC-158D	640 (290)	800 (363)	2.50 (63)	2.79 (71)	70 (32)	80 (36)	140 (63)	160 (72)	• •

Loading Table Description

Beam Loads: Table lists the total allowable load for various simple spans based on a minimum safety factor 2:1. If load is concentrated at center of span, multiply the load from the table by 0.5 and the corresponding deflection by 0.8.

Column Loads: Table lists the total allowable axial load for various unsupported column heights based on a minimum safety factor of 3:1. Eccentric loads should be reduced according to standard practice.

Notes: All beams should be supported in a manner to prevent rotation at supports. Long, deep beams should be tied between supports to prevent twist.
 * = Deflection is in excess of 3.00 In. (76mm); mid-span support is recommended.
 NR = Not Recommended

Enduro DuroStrut™ Guide Specification

1.0 Scope

1.1 This specification covers the requirements for Enduro Composite System's non-metallic Channel Framing Systems & Accessories.

2.0 Standards

2.1 All channel shall have a flame spread rating of 25 or less, and the Smoke Developed Index shall have a density of 450 or less when tested in accordance with the provisions of ASTM E-84; therefore qualifying as a class 1 material in the Uniform Building Code.

2.2 All channel shall have a Nexus polyester surfacing veil over the entire surface in addition to a UV inhibitor in the resin system to protect against degradation from ultra-violet light.

3.0 Materials

3.1 All channel shall be manufactured by the pultrusion process, and contain a minimum of 50% glass by weight.

3.2 All channel shall conform, as a minimum requirement, to loads and deflections shown on the tables in the latest version of the Enduro Composite System technical catalog.

4.0 Non-Metallic Pipe Clamps

4.1 All pipe clamps shall be manufactured by the injection molding process with an impact modified, 30% glass filled thermoplastic polyester resin.

4.2 All pipe clamps interlock with the channel framing described above.

4.3 All pipe clamps shall be designed for rigid PVC coated steel, Schedule 40 or 80 PVC, and filament wound fiberglass pipe or conduit. Clamps shall be adjustable to accommodate a 3/4" minimum deviation in O.D. size.

5.0 Fasteners


5.1 All fasteners shall be injection molded glass reinforced nylon, 316 stainless steel, or pultruded vinyl ester rod with ground threads and compression molded vinyl ester nuts.

6.0 Acceptable Manufacturer

6.1 DuroStrut™ is manufactured and fabricated exclusively by Enduro Composite Systems – Houston, TX.

DuroThread™

INSTALLATION GUIDE



The DuroThread™ fastener system is a vinyl ester resin and fiberglass composite with unique characteristics which make it ideal for many applications where high strength, non-metallic fasteners are required.

Size	Thread Shear (single nut) Lbs.	Maximum Installation Torque	Socket Size In.
3/8" – 16 UNC	1,250	4 Ft.-Lbs.	15/16
1/2" – 13 UNC	2,200	8 Ft.-Lbs.	15/16
5/8" – 11 UNC	3,100	16 Ft.-Lbs.	15/16
3/4" – 10 UNC	4,500	24 Ft.-Lbs.	15/16
1" – 10 UNC	6,500	50 Ft.-Lbs.	2

Installation Instructions

For Access After Installation

If the assembly will require occasional removal of the nuts, the rod should be lightly coated with a dry lubricant, silicon spray, or a light oil prior to assembly.

For Permanent Installation

If the assembly is designed to be a permanent installation, the nuts and studs should be bonded with an epoxy adhesive. Apply a light coating of adhesive to the stud and nut threads, then quickly secure the assembly before adhesive has time to set, otherwise the mil thickness of the adhesive will make it impossible to thread. Next, apply a thick coat of adhesive to the exposed stud and nut surfaces. This provides a locking mechanism which eliminates the need for extra torque and lock washers.

For Hanging System Installation

The optimum method of installation for a hanger system is to finger tighten the assembly and then only tighten the nuts one-half turn to secure any jam nut assemblies. Follow the permanent installation procedure whenever possible. This results in minimum torque and allows maximum thread shear.

To insure maximum resistance to chemical attack once the assembly is completed, the exposed stud thread and nut surfaces should be coated with EnduroSeal™ (Part No. ES-Q or ES-G; see page 2).

Metal and FRP Installation

When utilizing metal fasteners, connectors, or nuts, consideration must be given to reduced strengths. DuroThread™ rod and nuts are designed with maximum thread engagement and extra nut thickness. Metal products have less thread engagement. When installation requires metal components, special tests may be necessary to define ultimate strengths of the fastener systems.

For Beam Clamp Installation

Maximum installation torque of 10 foot-pounds is recommended to secure set screw.

Site Conditions

Vibration and dynamic loading conditions on the DuroThread™ assembly should be eliminated or minimized. If this is not possible, additional safety factors should be used in designing the fastener system.

Tools Required

The oversize hex nut design of the DuroThread™ nut requires a larger than normal socket wrench, but either a six point or twelve point socket will work.

Important – do not exceed the torque values listed in the table on the left.

Caution


Do not over torque the DuroThread™ nut and rod. The thread shear and torque values are NOT mutually exclusive, they are additive.

Example:

1/2" – 13 has a thread shear of 2,200 Lbs. and an ultimate torque strength of 18 foot-pounds. If you use the maximum installation torque of 8 foot-pounds, the amount of thread shear remaining is reduced to 1,225 pounds.

Specifying engineers should apply this information at the design stage, applying the proper safety factors to ensure a secure installation.

Typical Hanging Support System



EFFECT OF TEMPERATURE FRP

Strength properties of reinforced plastics are reduced when continuously exposed to elevated temperatures. Working loads shall be reduced when based on the following:

Temperatures in Degree F	Polyester Resin % of Strength	Vinyl Ester Resin % of Strength
75	100	100
100	90	100
125	78	100
150	68	90
175	60	90
200	52	75

Note: Percentages shown are approximate. If unusual temperature conditions exist, the manufacturer should be consulted. Below freezing temperatures do not adversely affect the load rating capability of the tray. Fiberglass does not become brittle at below freezing temperatures. Careful review should be made of applications involving service temperatures over 200°F.

The test values in the following chart were obtained from tests conducted by Enduro's vinyl ester resin supplier. The values shown, although obtained from an actual coupon test, are intended for illustrative purposes only, and not for use in design calculations. The values for polyester are slightly lower.

Test Temp. °F	-100	-50	0	50	77	100	150	200	250	300
Table 3 Flex. St., PSI, ASTM D790	101,500	86,400	79,500	72,300	68,100	66,300	58,700	27,400	13,200	9,200
Flex. Mod., PSI x 10 ⁶ , ASTM D790	3.36	3.32	3.42	3.38	3.24	3.29	3.07	1.98	0.98	0.83
Tensile St., PSI, ASTM D638	84,100	70,400	63,900	58,000	56,100	54,600	49,900	41,800	29,600	22,000

CORROSION RESISTANCE RESIN SYSTEMS

where strong acids (such as hydrochloric acid), strong alkalis (such as caustic soda), organic solvents and halogenated organic conditions exist. An abbreviated Guide is provided below to assist in the selection of the proper resin system for individual application.

Two standard composite resin systems are available. For most applications, isophthalic polyester fire-retardant (FR-P) is the more widely used. A vinyl ester composite fire-retardant resin system (FR-VE) is recommended

All composite material has an ultra-violet light inhibiting chemical additive and has a maximum flame spread of 25 or less, per ASTM E-84 (Class 1 flame spread). All pultruded products have complete Nexus Veil Coverage (outer surfacing fabric) to provide maximum chemical and UV protection.

Table 4 Corrosion Resistance Guide

Chemicals	75°F	160°F	Chemicals	75°F	160°F
Acetic Acid 5%	FR-P	FR-P	Methyl Alcohol 10%	FR-P	FR-VE-150° (*)
Acetic Acid 25%	FR-P	FR-VE-210° (*)	Naphtha	FR-P	FR-P
Aluminum Potassium Sulfate 5%	FR-P	FR-P	Nitric Acid 5%	FR-P	FR-P
Ammonium Hydroxide 10%	FR-P	FR-VE-150°	Nitric Acid 20%	FR-VE	FR-VE-120° (*)
Ammonium Nitrate	FR-P	FR-P	Phosphoric Acid 10%	FR-P	FR-P
Benzenesulfonic Acid 5%	FR-P	FR-P	Phosphoric Acid 30%	FR-P	FR-P
Calcium Chloride	FR-P	FR-P	Phosphoric Acid 85%	FR-P	FR-P
Carbon Tetrachloride	FR-VE	FR-VE-100° (*)	Sodium Bicarbonate 10%	FR-P	FR-P
Chlorine Dioxide 15%	FR-P	FR-VE 150° (*)	Sodium Bisulfate	FR-P	FR-P
Chromic Acid 5%	FR-P	FR-VE 150° (*Call)	Sodium Carbonate	FR-P	FR-VE
Copper Sulfate	FR-P	FR-P	Sodium Chloride	FR-P	FR-P
Diesel Fuel No. 1	FR-P	FR-P	Sodium Hydroxide 1-50%	FR-VE	FR-VE-120° (*)
Diesel Fuel No. 2	FR-P	FR-P	Sodium Hypochlorite 5%	FR-P	FR-VE-120° (*)
Ethylene Glycol	FR-P	FR-P	Sodium Nitrate	FR-P	FR-P
Fatty Acids 100%	FR-P	FR-P	Sodium Silicate	FR-P	FR-VE-210° (*)
Ferrous Sulfate	FR-P	FR-P	Sodium Sulfate	FR-P	FR-P
Fluosilicic Acid 0-20%	FR-VE	FR-VE (Call)	Sulfuric Acid 0-30%	FR-P	FR-P
Hydrochloric Acid 1%	FR-P	FR-P	Sulfuric Acid 30-50%	FR-VE	FR-VE
Hydrochloric Acid 15%	FR-P	FR-VE-180° (*)	Sulfuric Acid 50-70%	FR-VE	FR-VE-180° (*)
Hydrochloric Acid 37%	FR-P	FR-VE-150° (*)	Trisodium Phosphate 25%	FR-P	FR-VE-210° (*)
Hydrogen Sulfide	FR-P-140°	FR-VE-210°	Trisodium Phosphate - All	FR-VE	FR-VE-210° (*)
Kerosene	FR-P	FR-P	Water, Distilled	FR-P	FR-P
Magnesium Chloride	FR-P	FR-P			

FR = Fire-Retardant P = Polyester Resin VE = Vinyl Ester Resin (*) = Not recommended to exceed this temperature. Call = Call for recommendations

Information contained in this chart is based on data from raw material suppliers and collected from several years of actual industrial applications.

Temperatures are not the minimum nor the maximum (except where specifically stated) but represent standard test conditions. The products may be suitable at higher temperatures, but individual test data should be required to establish such suitability.

The recommendations or suggestions contained in this chart are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory or by actual field trial prior to use.

TYPICAL PROPERTIES FRP STRUCTURAL SHAPES

Table 5

Mechanical (coupon)	FR-P	FR-VE	Mechanical (coupon)	FR-P	FR-VE
Longitudinal Direction			Transverse Direction		
Ultimate Tensile Strength, PSI (ASTM D638)	30,000	35,000	Ultimate Tensile Strength, PSI	7,000	10,000
Ultimate Compressive Strength, PSI (ASTM D695)	30,000	35,000	Ultimate Compressive Strength, PSI	15,000	20,000
Ultimate Flexural Strength, PSI (ASTM D790)	30,000	35,000	Ultimate Flexural Strength, PSI	10,000	14,000
Tensile Modulus, PSI x 10 ⁶	2.5	3.0	Tensile Modulus, PSI x 10 ⁶	0.8	1.0
Compressive Modulus, PSI x 10 ⁶	2.5	2.5	Compressive Modulus, PSI x 10 ⁶	1.0	1.2
Flexural Modulus, PSI x 10 ⁶	1.6	2.0	Flexural Modulus, PSI x 10 ⁶	0.8	1.0
Ultimate Shear Strength, PSI	5,500	7,000	Ultimate Shear Strength, PSI	5,500	6,000
Ultimate Bearing Stress, PSI	30,000	35,000	Ultimate Bearing Stress, PSI	30,000	35,000
Izod Impact Strength, Ft.-Lbs. per inch of notch (ASTM D256)			Izod Impact Strength, Ft.-Lbs. per inch of notch (ASTM D256)	4	5
(sample thickness 1/8" except 1/4" for rod)	25	30	Barcol Hardness (ASTM D2583-75)	50	50
Electrical			Full Section in Bending		
Electric Strength, short term in oil, 1/8", vpm (ASTM D149)*	200	200	Modulus of Elasticity, PSI x 10 ⁶	2.5	3.0
Electric Strength, short term in oil, KV per inch	35	35	Tensile Strength, PSI	20,000	25,000
Dielectric Constant, 60 Hz. (ASTM D150)*	5.6	5.2	Compressive Strength, PSI	20,000	25,000
Dissipation Factor, 60 Hz. (ASTM D150)*	0.03	0.03	Thermal		
Arc Resistance, seconds (ASTM D495)**	120	120	Thermal Coefficient of Expansion, Inches/Inch/°F (ASTM D696)**	5 x 10 ⁻⁶	5 x 10 ⁻⁶
Fire Retardant Properties			Thermal Conductivity, BTU per Sq. Ft./Hr./°F/In. (ASTM C-1776-76)	4	4
Flame Resistance, ign/burn, seconds (FTMS 406-2023)	75/75	75/75	Specific Heat, BTU/Lb./°F	0.28	0.28
Intermittent Flame Test, rating (HLT-15)	100	100	Other		
Flammability Test, average time of burning 5 seconds, average extent of burning 15mm (ASTM D635)			Density, Lbs./In. ³ (ASTM D792)	0.065	0.065
Surface Burning Characteristics, maximum (ASTM E84)	15	15	Specific Gravity (ASTM D792)	1.80	1.80
			Water Absorption, Max. % by weight (24 hour immersion) (ASTM D570)	.50	.50

* Specimen tested perpendicular to laminate face. Note: 1 PSI = 6.894 K Pa, 1 Ft. - Lb./In. = 5.443 kg - m/m

** Indicates reported value measured in longitudinal direction.

Note: Depending on the specific glass content and resin, the strength and stiffness properties may be significantly higher.

TYPICAL PROPERTIES FRP THREADED ROD

Table 6

For additional information Refer to DuroStrut® Installation Guide on page 6.

Properties	3/8 -16 UNC	1/2 -13 UNC	5/8 -11 UNC	3/4 -10 UNC	1-8 UNC
Thread shear strength using fiberglass nut in tensile - Lbs.	1,250	2,200	3,100	4,500	6,500
Transverse shear on threaded rod - double shear (load Lb.) (ASTM-B565)	3,000	5,000	7,500	12,000	22,000
Transverse shear on threaded rod - single shear (load Lb.)	1,600	2,600	3,800	6,200	15,000
Compressive strength longitudinal, PSI (ASTM-D695)	54,000	54,000	54,000	54,000	65,000
Flexural strength, PSI (ASTM-D790)	55,000	55,000	55,000	55,000	60,000
Flexural modulus, PSI x 10 ⁶ (ASTM-D790)	2.0	2.0	2.0	2.50	2.75
Torque strength using fiberglass nut lubricated with SAE 10W30 motor oil, Ft.-Lbs.	8	18	35	50	110
Dielectric strength, KV/In. (ASTM-D149)	35	35	35	35	35
Water absorption 24 hour immersion - threaded, % (ASTM-D570)	1	1	1	1	1
Coefficient of thermal expansion - longitudinal In./In./°F	5 x 10 ⁻⁶	5 x 10 ⁻⁶	5 x 10 ⁻⁶	5 x 10 ⁻⁶	5 x 10 ⁻⁶
Max recommended operation temp - based on 50% retention of ultimate thread shear strength °F	200	200	200	200	200
Stud weight, Lb./Ft.	0.07	0.12	0.18	0.28	0.50
Flammability	Self-extinguishing on all.				

Note: 1 Ft.-Lb. = .138 kg-M; 1 Lb = .4536 kg, 1 PSI = 6.984 K Pa

The following applies to Tables 5 and 6

1. Refer to Table 5 (FR-VE Resin) for fire retardant properties of threaded rod.
2. Test results are for studs with single nuts only. Proper safety factors should be applied to testing.
3. All values are based on laboratory test results.


DuroStrut™

Also from enduro

StandFast™

Fiberglass/Composite Instrument & Pushbutton Stands


A universal instrument support system that offers many of the same features and benefits as our cable tray, strut and wireway systems. Constructed from 2" Schedule 80 gray vinyl ester pipe with an 8" gray square vinyl ester base. Available in a variety of combinations to fit any mounting requirements. Delivered fully assembled, or available in component parts for field assembly.



INSTRUMENT SUPPORTS


Floor Mount Single

Catalog No.:
DISR170B1x(Dim. A)
Example: DISR170B148




Column or Wall Mount

Catalog No.:
DISR175B48 x (Dim. A) x (Dim. B)
Example: DISR175B48x11x12




Floor Mount Double

Catalog No.:
DISR171B x (Dim. A) x (Dim. B) x (Dim. C)
Example: DISR171B48x36x18




Floor Mount Multiple Instrument

Catalog No.:
DISR172B x (Dim. A) x (Dim. B) x (Dim. C)
Example: DISR172B36x12x15



FR-VE PUSHBUTTON STATION


- Made of pultruded fiberglass reinforced vinyl ester 2" square tube with an 8" vinyl ester base.
- Please specify dimensions in inches.



Catalog No.:
DPSx(Dim. A)x(Dim. B)x(Dim. C)
Example: DPS48x16x40

U-BOLTS

- Made from glass reinforced polyurethane resin, U-Bolts are the ideal choice for mounting enclosures, instrumentation, conduit, and piping on your StandFast™ support systems.
- Excellent as an alternative when replacing corroded steel U-Bolts.
- Recommended for operating temperatures up to 150°F.
- Four nuts included with each U-Bolt.



Part Number	Pipe Nom. Dia. In.	A	B	C	D	TL	Maximum Rec. Loading Lbs.	Maximum Rec. Torque In.-Lbs.
EU050	1/2	0.93	0.375	1.56	2.41	1.25	75	20
EU075	3/4	1.12	0.375	1.66	2.60	1.25	75	20
EU100	1	1.37	0.375	1.78	2.85	1.25	75	20
EU125	1 1/4	1.68	0.375	1.94	3.16	1.25	75	20
EU150	1 1/2	2.00	0.375	2.10	3.47	1.25	75	20
EU200*	2	2.43	0.500	2.46	4.18	1.50	150	40
EU250	2 1/2	2.93	0.500	2.71	4.68	1.50	150	40
EU300	3	3.56	0.500	3.03	5.31	1.50	150	40
EU350	3 1/2	4.06	0.500	3.28	5.81	1.50	150	40
EU400	4	4.56	0.500	3.53	6.31	1.50	150	40