

<b>TYPICAL PROPERTIES OF TURCITE® A and X</b>			
<b>ASTM or UL test</b>	<b>Property</b>	<b>Turcite® A</b>	<b>Turcite® X</b>
<b>PHYSICAL</b>			
D792	Density (lb/in <sup>3</sup> ) (g/cm <sup>3</sup> )	0.054 1.49	0.053 1.46
D570	Water Absorption, 24 hrs (%)	0.2	0.2
<b>MECHANICAL</b>			
D638	Tensile Strength @ Break (psi)	7,600	5,900
D638	Tensile Elongation at Break (%)	15	19
D790	Flexural Strength (psi)	11,000	8,000
D790	Flexural Modulus (psi)	350,000	335,000
D695	Compressive Strength (psi)	13,000	12,000
D785	Hardness, Rockwell	M81	M63
D256	IZOD Notched Impact (ft-lb/in)	0.57	0.54
<b>THERMAL</b>			
D696	Coefficient of Linear Thermal Expansion (x 10 <sup>-5</sup> in./in./°F)	5.2	5.2
D648	Heat Deflection Temp (°F / °C) at 264 psi	205 / 96	203 / 95
-	Max Operating Temp (°F / °C)	180 / 82	180 / 82
<b>TRIBOLOGICAL</b>			
*	Wear Factor @ 73°F (in/psi-fpm-hr)	43 x 10 <sup>-10</sup>	30 x 10 <sup>-10</sup>
*	Coefficient of Friction, Dynamic (non-lubricated)	0.30	0.22
*	Limiting PV @ 100 fpm (psi-fpm)	7,500	16,000

These products are available from

