

Authorized Distributor:

Aetna Plastics Corp.

1702 St. Clair Ave. Cleveland, Ohio 44114

Tel: 800-634-3074 • 216-781-4421 • Fax: 216-781-4474

E-mail: sales@aetnaplastics.com • Web site: www.aetnaplastics.com

Series 11900 Contact Molded FRP Composite Fire Retardant Pipe, Duct and Fittings

**For corrosive industrial and environmental
service, where both excellent corrosion
resistance and fire retardancy are important.**

Uses and applications:

Corrosion resistant fume duct
Chemical process piping
Acid Drains
Severe service chemical applications
Floor collection drains
Organic chemicals
Process plant piping
Oxidizing chemicals and acids
Excellent physical properties to 230° F.
An alternative to costly alloys and specialty metals
General industrial service for corrosive liquids and gases

Description: Composition:

Contact molded fiberglass reinforced fire retardant vinylester composite pipe and duct. NBS PS-15-69 Classification. Nominal 10 mil C-Veil and/or Nexus reinforced inner corrosion barrier, followed by a nominal 86 mil corrosion liner reinforced with fiberglass chopped strand reinforcement, followed by a structural laminate reinforced with fiberglass woven roving and/or fiberglass chopped strand reinforcement. The exterior of the pipe and duct will be post-coated after fabrication with a UV resistant polymer coating.

A premium grade fire retardant vinylester resin (Derakane 510, Reichhold 9300, or equal), is used for the corrosion barrier/liner. The same premium grade fire retardant vinylester resin, pigmented dark grey for UV inhibition, is used for the pipe and duct structural wall laminate. Antimony trioxide is added to the resin to achieve an ASTM E-84 Class I flame spread rating of 25, or less.

Pipe Sizes: Pipe Lengths:

137+ different diameters, ranging from a tiny 3/8" dia. up to a mammoth 144" dia. Pipe and duct available built to iron pipe outside diameters (ASTM D- 2996, Table 3), as well as pipe and duct built to chemical process piping inside diameter standards. A current list of pipe and duct sizes is available upon request. New sizes are being added regularly.

1/2" dia. pipe and smaller is built in 5 ft. lengths.
3/4" & 7/8" dia. pipe is built in 7 ft. lengths.
1" through 1-1/2" dia. pipe is built in 10 ft. lengths.
2" through 6" dia. pipe is available in 20 ft. lengths.
8" dia through 144" dia. pipe is available in 20 and 40 ft. lengths.

Performance: Good corrosion resistance over a wide temperature range. Temperatures from sub-zero to 230 °F.

Advantages: Working pressures from NBS-PS-15-69 duct to 150 psi+, depending upon size and wall thickness.

Vacuum to -14.7 psig for all sizes, by selection of wall thicknesses and/or stiffening ribs.

Available for earth burial, all depths, with selection of wall thicknesses, ribs and glass content.

Weighs 1/6 as much as steel. Thus, lower installed costs.

Series 11900 pipe and duct can be provided using resins that meet the requirements of F.D.A. regulations 21-CFR-175.105 and 21-CFR 177.242.

Smooth inner surface produces very low frictional loss for reduced pumping and fan blower costs. Hazen-Williams flow coefficient of 150.

Recommended for a wide range of corrosion applications. Consult with Industrial Fiberglass Specialties, or the resin manufacturer, for specific project recommendations.

Joining systems: Bell (socket) and spigot structural adhesive weld bonded joints. Adhesive bonded joints are available as your choice of straight/straight, straight/taper and taper/taper.

Threaded joints (NPT) through 12" dia. Other thread configurations available upon special order.

Flanges, including superior filament wound construction, available in all sizes through 84" dia. ANSI 150 lb., 300 lb. and 600 lb. all available as standard. Any pressure rating and drilling pattern available on order.

Van Stone, loose ring style, flanges.

Flange Spacers - all diameters, bolt hole patterns and thicknesses, built to order.

Bell and spigot O-Ring joints, thru 84" dia.

Bell and spigot O-Ring joints with locking key for restrained ends.

Mechanical Couplings, including Victaulic and Taylor-Kerr.

Repair (maintenance) couplings.

Physical Properties: See Table 1 for typical physical, thermal, and fire properties of Series 11900 Contact Molded FRP Composite Pipe and Duct. These are conservative properties that can be used for the design of pipe for pressure, vacuum, supported span and burial conditions. Contact Industrial Fiberglass Specialties for recommendations on the appropriate design formulas to be used for FRP composite pipe and duct.

Mechanical Properties:

Burial installations: As a custom manufacturer of pipe and fittings, we can design and build pipe and duct to handle burial conditions ranging from live loads due to highway and rail traffic - to earth loads of 100 ft. or greater. We even have experience with underwater installations. Our engineers will welcome the opportunity to work with you on a pipe design, backfill selection and installation methods to meet your specific requirements. The result will be your lowest cost per year of service life (installed basis).

Supported span installations: Again, we can design and build pipe and duct to provide you the lowest cost for supported span installations. Since we are not limited to just a few pipe wall thicknesses and laminate constructions - we can select and choose the combination of pipe and duct design, and support designs, that will provide your "best buy" costs. Consult with our engineers for help with your specific requirements.

Fittings:

Elbows, standard are 22-1/2°, 30°, 45° and 90°. Any angle elbow available on special order. Elbows through 48" dia. are available as smooth radius. Mitered elbows are available in all sizes.

Reducing Elbows

Tees, Reducing Tees

Concentric Taper Body Reducers

Eccentric Taper Body Reducers

Saddles, with FRP and stainless steel threaded outlets, bell outlets, spigot outlets and flanged outlets

Wear pads (blank saddles)

Crosses, Reducing Crosses

Laterals, Reducing Laterals

True Wyes.

Round to Rectangular Transitions

P-Traps and 180° U-Bends

Floor Drains

Expansion Joints

Pipe couplings, Threaded (NPT) couplings

Adapters, bell by NPT thread (male or female threads available)

Adapters, spigot by NPT thread (male or female threads available)

Pipe and threaded nipples

Reducing bushings and threaded adapter bushings

Fitting and pipe plugs and pipe caps

Blind Flanges, Threaded Flanges

Reducing Flanges, Orifice Flanges

All fittings are available as adhesive socket, plain end, flanged end, bell and spigot O-Ring; or any combination. See full Industrial Fiberglass Specialties" catalog for sizes, dimensions and tolerances. Fittings and flanges are available from 3/8" dia. through 84" dia. We welcome the opportunity to work with our customers on special fittings.

Table 1

INDUSTRIAL FIBERGLASS SPECIALTIES, INC

521 Kiser Street - Dayton, OH 45404-1641

Telephone (937) 222-9000 - Fax (937) 222-9020

Properties of Series 11900 Contact Molded FRP Pipe & Duct

Corrosion Barrier	10 mil Veil Reinforced
Corrosion Liner	86 mil Fiberglass Chopped Strand Mat
Resin (barrier/Liner)	Fire Retardant Vinylester Resin
Structural Wall	Alternating Glass Mat & Woven Roving
Resin (FW Overwrap)	Fire Retardant Vinylester Resin

Laminate Elastic and Strength Properties per ASTM D3299 (40% glass content)

Flexural Strength	31,700 psi
Flexural Modulus	1,530,000 psi
Tensile Strength	26,600 psi
Tensile Modulus	2,160,000 psi
Tensile Elongation	1.9%

Thermal, Fire, and Smoke Properties for Typical Contact Molded Laminates

Thermal Conductivity	1.5 BTU/hr./sq. ft./deg. F/in. thick.
Coefficient of Thermal Expansion	0.0000219/in/in/deg. C
Flame Spread Value (ASTM E-84)	< 25
Smoke Generation Value (ASTM E-84)	>750
Autoignition Temperature	approx 800 deg. F.

Typical Clear Casting Properties

Tensile Elongation (at break)	greater than 4.0%
Barcol Hardness	35 to 40
Heat Distortion Temperature (HDT)	230 deg. F
Specific Gravity	1.26
Volumetric Shrinkage	7.7%
Average Dielectric Constant (ASTM D150)	3.39
Electrical Dissipation Factor (ASTM D150)	0.04