

## Quadrant EPP TIVAR® 88 Premium, Glass Filled, Crosslinked Lining Material

Physical Properties	Metric	English	Comments
Specific Gravity	0.93 g/cc	0.0336 lb/in <sup>3</sup>	ASTM D792
Water Absorption	Max 0.01 %	Max 0.01 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	Max 0.01 %	Max 0.01 %	Immersion; ASTM D570(2)
<b>Mechanical Properties</b>			
Hardness, Shore D	69	69	ASTM D2240
Tensile Strength, Ultimate	38.6 MPa	5600 psi	ASTM D638
Elongation at Break	300 %	300 %	ASTM D638
Tensile Modulus	0.703 GPa	102 ksi	ASTM D638
Flexural Modulus	0.745 GPa	108 ksi	ASTM D790
Flexural Yield Strength	20.7 MPa	3000 psi	ASTM D790
Compressive Strength	20.7 MPa	3000 psi	10% Def., 73°F; ASTM D695
Compressive Modulus	0.483 GPa	70 ksi	ASTM D695
Coefficient of Friction	0.12	0.12	Dry vs. Steel; QTM55007
Limiting Pressure Velocity	0.0701 MPa-m/sec	2000 psi-ft/min	4:1 safety factor; QTM 55007
Izod Impact, Notched	NB	NB	ASTM D256 Type A
<b>Electrical Properties</b>			
Surface Resistivity per Square	Min 1e+015 ohm	Min 1e+015 ohm	ASTM D257
Dielectric Constant	2.3	2.3	(1MHz); ASTM D150
Dielectric Strength	90.6 kV/mm	2300 V/mil	Short Term; ASTM D149
Dissipation Factor	0.0005	0.0005	(1MHz); ASTM D150
<b>Thermal Properties</b>			
CTE, linear 68°F	324 µm/m-°C	180 µin/in-°F	(-40°F to 300°F); ASTM E831
Thermal Conductivity	0.409 W/m-K	2.84 BTU-in/hr-ft <sup>2</sup> -°F	
Melting Point	135 °C	275 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	82.2 °C	180 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	46.7 °C	116 °F	ASTM D648
Flammability, UL94 (Estimated Rating)	HB	HB	1/8 inch
<b>Qualitative Processing Properties</b>			
Compliance - FDA	Not Compliant		
Machinability	3		1-10, 1=Easier to Machine
Service in Alcohols	Acceptable		
Service in Aliphatic Hydrocarbons	Acceptable		
Service in Aromatic Hydrocarbons	Unacceptable		
Service in Chlorinated Solvents	Acceptable		
Service in Ethers	Limited		
Service in Ketones	Limited		
Service in Strong Acids	Limited		
Service in Strong Alkalies	Acceptable		
Service in Sunlight	Limited		

These products are available from

**AP**  
**Aetna Plastics**  
 800.634.3074 - www.aetnaplastics.com

Service in Weak Acids

Acceptable

Service in Weak Alkalies

Acceptable

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that Quadrant EPP and Automation Creations, Inc. cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of Quadrant EPP's products in any given application.

These products are available from

**AP**  
**Aetna Plastics**  
800.634.3074 - [www.aetnaplastics.com](http://www.aetnaplastics.com)