

Quadrant EPP TIVAR® 88 W/BurnGuard - Flame Retardant Lining Material

Physical Properties	Metric	English	Comments
Specific Gravity	1 g/cc	0.0361 lb/in ³	ASTM D792
Water Absorption	Max 0.01 %	Max 0.01 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	Max 0.01 %	Max 0.01 %	Immersion; ASTM D570(2)
Mechanical Properties			
Hardness, Shore D	64	64	ASTM D2240
Tensile Strength, Ultimate	24.8 MPa	3600 psi	ASTM D638
Elongation at Break	120 %	120 %	ASTM D638
Tensile Modulus	0.641 GPa	93 ksi	ASTM D638
Flexural Modulus	0.641 GPa	93 ksi	ASTM D790
Flexural Yield Strength	19.3 MPa	2800 psi	ASTM D790
Compressive Strength	19.3 MPa	2800 psi	10% Def., 73°F; ASTM D695
Compressive Modulus	0.448 GPa	65 ksi	ASTM D695
Coefficient of Friction	0.09	0.09	Dry vs. Steel; QTM55007
Limiting Pressure Velocity	0.0701 MPa-m/sec	2000 psi-ft/min	4:1 safety factor; QTM 55007
Izod Impact, Notched	NB	NB	ASTM D256 Type A
Electrical Properties			
Surface Resistivity per Square	Min 1e+012 ohm	Min 1e+012 ohm	ASTM D257
Thermal Properties			
CTE, linear 68°F	288 µm/m-°C	160 µin/in-°F	(-40°F to 300°F); ASTM E831
Melting Point	135 °C	275 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	82.2 °C	180 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	46.7 °C	116 °F	ASTM D648
Flammability, UL94 (Estimated Rating)	V-0	V-0	1/8 inch
Qualitative Processing Properties			
Compliance - FDA	Not Compliant		
Machinability	3		1-10, 1=Easier to Machine
Service in Alcohols	Acceptable		
Service in Aliphatic Hydrocarbons	Acceptable		
Service in Aromatic Hydrocarbons	Unacceptable		
Service in Chlorinated Solvents	Acceptable		
Service in Ethers	Limited		
Service in Ketones	Limited		
Service in Strong Acids	Limited		
Service in Strong Alkalies	Acceptable		
Service in Sunlight	Limited		
Service in Weak Acids	Acceptable		
Service in Weak Alkalies	Acceptable		

These products are available from


Aetna Plastics
 800.634.3074 - www.aetnaplastics.com

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that Quadrant EPP and Automation Creations, Inc. cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of Quadrant EPP's products in any given application.