

## Quadrant EPP TIVAR® 88 ESD - Premium Glass Filled, Crosslinked ESD Lining Material

Physical Properties	Metric	English	Comments
Specific Gravity	0.945 g/cc	0.0341 lb/in <sup>3</sup>	ASTM D792
Water Absorption	Max 0.01 %	Max 0.01 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	Max 0.01 %	Max 0.01 %	Immersion; ASTM D570(2)
<b>Mechanical Properties</b>			
Hardness, Shore D	67	67	ASTM D2240
Tensile Strength, Ultimate	33.1 MPa	4800 psi	ASTM D638
Elongation at Break	250 %	250 %	ASTM D638
Tensile Modulus	0.772 GPa	112 ksi	ASTM D638
Flexural Modulus	0.772 GPa	112 ksi	ASTM D790
Flexural Yield Strength	22.8 MPa	3300 psi	ASTM D790
Compressive Strength	20.7 MPa	3000 psi	10% Def., 73°F; ASTM D695
Compressive Modulus	0.6 GPa	87 ksi	ASTM D695
Coefficient of Friction	0.14	0.14	Dry vs. Steel; QTM55007
Limiting Pressure Velocity	0.0701 MPa-m/sec	2000 psi-ft/min	4:1 safety factor; QTM 55007
Izod Impact, Notched	NB	NB	ASTM D256 Type A
<b>Electrical Properties</b>			
Surface Resistivity per Square	1e+006 - 1e+009 ohm	1e+006 - 1e+009 ohm	ASTM D257
<b>Thermal Properties</b>			
CTE, linear 68°F	324 µm/m-°C	180 µin/in-°F	(-40°F to 300°F); ASTM E831
Melting Point	135 °C	275 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	82.2 °C	180 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	46.7 °C	116 °F	ASTM D648
Flammability, UL94 (Estimated Rating)	HB	HB	1/8 inch
<b>Qualitative Processing Properties</b>			
Compliance - FDA	Not Compliant		
Machinability	3	1-10, 1=Easier to Machine	
Service in Alcohols	Acceptable		
Service in Aliphatic Hydrocarbons	Acceptable		
Service in Aromatic Hydrocarbons	Unacceptable		
Service in Chlorinated Solvents	Acceptable		
Service in Ethers	Limited		
Service in Ketones	Limited		
Service in Strong Acids	Limited		
Service in Strong Alkalies	Acceptable		
Service in Sunlight	Limited		
Service in Weak Acids	Acceptable		
Service in Weak Alkalies	Acceptable		

These products are available from

  
**Aetna Plastics**  
 800.634.3074 - www.aetnaplastics.com

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that Quadrant EPP and Automation Creations, Inc. cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of Quadrant EPP's products in any given application.

These products are available from



**Aetna Plastics**

800.634.3074 - [www.aetnaplastics.com](http://www.aetnaplastics.com)